

<b>THOMSON</b> <b>DELPHION</b>		<b>RESEARCH</b>	<b>PRODUCTS</b>	<b>INSIDE DELPHION</b>
<a href="#">Home</a>	<a href="#">Web Files</a>	<a href="#">My Account</a>   <a href="#">Products</a>	Search: <a href="#">Quick/Number</a> <a href="#">Boolean</a> <a href="#">Advanced</a> <a href="#">Derwent</a>	

## The Delphion Integrated View

Get Now: ☒ PDF | [More choices...](#)

Tools: Add to Work File: [Create new Work File](#)

View: [INPADOC](#) | Jump to: [Top](#)

[Email this to a](#)

Title: **JP56028463A2: WAX COATING METHOD OF LAMINATED FASTENED CELL ELEMENT**

Country: **JP Japan**

Kind: **A**

Inventor: **TSUCHIDA TAKASHI;  
SATO MASANORI;  
MATSUOKA KUNIHIRO;**

Assignee: **FUJI ELELCTROCHEM CO LTD**  
[News, Profiles, Stocks and More about this company](#)

Published / Filed: **1981-03-20 / 1979-08-14**

Application Number: **JP1979000103391**

IPC Code: **H01M 2/02;**

Priority Number: **1979-08-14 JP1979000103391**

Abstract: **PURPOSE:** To form a complete wax coating by placing a laminated fastened battery element and wax bath in a same evacuated atmosphere, and then soaking the battery in the bath while simultaneously releasing the evacuation.

**CONSTITUTION:** A laminated fastened battery element and wax bath is placed in a same evacuated atmosphere, for example of 100~30mmHg. For example, the wax bath is a molten mixture of 15pts.wt. of vinyl acetate-ethylene copolymer having a low molecular weight, a softening point of 60~90°C, and low viscosity and containing about 30% of vinyl acetate and 85pts.wt. of micro crystalline wax. The laminated battery element is soaked in the bath heated at 125±2°C, and the atmosphere is released from evacuation or pressurized to cause the wax penetrate into small spaces completely.

**COPYRIGHT:** (C)1981,JPO&Japio


Family: **None**

**Best Available Copy**

Forward References:

**Go to Result Set:** [Forward references \(2\)](#)

PDF	Patent	Pub.Date	Inventor	Assignee	Title
	<a href="#">US6586912</a>	2003-07-01	Tsukamoto; Hisashi	Quallion LLC	<a href="#">Method and apparatus for amplitude limiting battery temperature spikes</a>
	<a href="#">US6074774</a>	2000-06-13	Semmens; Michael G.	Electrosorce, Inc.	<a href="#">Sealed recharge battery plenum stabilized with state changeable substance</a>



View  
Imac

1 pa

Other Abstract Info: None



[Nominate this for the Gallery...](#)



© 1997-2004 Thomson

[Research Subscriptions](#) | [Privacy Policy](#) | [Terms & Conditions](#) | [Site Map](#) | [Contact Us](#) | [Help](#)



(19)

(11) Publication number: **56028**

Generated Document.

**PATENT ABSTRACTS OF JAPAN**(21) Application number: **54103391**(51) Intl. Cl.: **H01M 2/02**(22) Application date: **14.08.79**

(30) Priority:

(43) Date of application  
publication: **20.03.81**(84) Designated contracting  
states:(71) Applicant: **FUJI ELELCTROCHEM CO L**(72) Inventor: **TSUCHIDA TAKASHI**  
**SATO MASANORI**  
**MATSUOKA KUNIHIRO**

(74) Representative:

**(54) WAX COATING  
METHOD OF LAMINATED  
FASTENED CELL ELEMENT**

(57) Abstract:

**PURPOSE:** To form a complete wax coating by placing a laminated fastened battery element and wax bath in a same evacuated atmosphere, and then soaking the battery in the bath while simultaneously releasing the evacuation.

**CONSTITUTION:** A laminated fastened battery element and wax bath is placed in a same evacuated atmosphere, for example of 100 ~ 30mmHg. For example, the wax bath is a molten mixture of 15pts.wt. of vinyl acetate-ethylene copolymer having a low molecular weight, a softening point of 60 ~ 90°C, and low viscosity and containing about 30% of vinyl acetate and 85pts.wt. of micro crystalline wax. The laminated battery element is soaked in the bath heated at 125±2°C, and the atmosphere is released from evacuation or

pressurized to cause the wax penetrate  
into small spaces completely.

COPYRIGHT: (C)1981,JPO&Japio